

# **GTS-PP**

## Factory Grade<sup>™</sup> 3LPP Field-Applied Coating System

Launched in 2000, the GTS-PP 3LPP coating system remains the world's leading joint coating for 3LPP coated pipelines. Its patented design uses Factory Grade<sup>™</sup> polypropylene materials to deliver equivalent performance to, and fusion to, the factoryapplied 3LPP coating with low installation temperatures and a proven and controlled application process.

#### Factory Grade<sup>™</sup> 3LPP Coating Technology

- **Polypropylene (PP)** top coat delivers mechanical protection and resistance to moisture absorption critical for high temperature and deepwater pipelines
- High temperature liquid epoxy or fusion bonded on steel provides Factory Grade<sup>™</sup> resistance to cathodic disbondment and allows for low installation temperatures
- **PP copolymer** layer bonds the PP top coat to the epoxy and fuses to the factory-applied coating to eliminate the possibility of moisture ingress

#### **Proven Compatibility and Fusion**

• Proven to provide consistent fusion to the factory-applied 3LPP coating with efficient installation

#### **Easy to Install with Process Control**

- Factory Grade<sup>™</sup> performance achieved with low installation temperatures using uniform induction pre-heating technology
- Can be installed directly by contractors, supported by Canusa-CPS' industry leading field service team
- Can be combined with the patented IntelliCOAT<sup>™</sup> systems, providing a fully automated, efficient and safe installation

#### **Engineered for Maximum Efficiency**

- Patented Reduced Edge Thickness design enhances installation efficiency and allows for elevated thickness applications
- Automated tube welding eliminates overlap/closure system typical of traditional sleeve systems, allowing for uniform thickness and cycle time reduction



### **Applications**



Onshore Pipelines



Offshore, Reel, J & S Lay



High Temperature



High Abrasion Environments



High Moisture Environments

## canusacps.com

**PRODUCT DATA SHEET** 

# **GTS-PP**

### Factory Grade<sup>™</sup> 3LPP Field-Applied Coating System

The product information shown here is intended as a guide for standard products.

Consult your Canusa representative for specific projects or unique applications.

Pipeline Operating Temp. Minimum Installation Temp. Main Line Coating Compatibility PP Copolymer Properties Melting point Lap Shear @ 23°C Lap Shear @ 110°C	ASTM D3418 EN 12068 EN 12068	Up to 140°C (284°F)* 175°C (347°F) 3LPP, FBE 147°C > 600 N/cm <sup>2</sup> > 100 N/cm <sup>2</sup>	GTS-PP can be combined with the patented IntelliCOAT™ system, providing a fully automated Factory Grade™ coating system.
Minimum Installation Temp. Main Line Coating Compatibility PP Copolymer Properties Melting point Lap Shear @ 23°C Lap Shear @ 110°C	ASTM D3418 EN 12068 EN 12068	175°C (347°F) 3LPP, FBE 147°C > 600 N/cm <sup>2</sup> > 100 N/cm <sup>2</sup>	the patented IntelliCOAT™ system, providing a fully automated Factory Grade™ coating system.
Main Line Coating Compatibility PP Copolymer Properties Melting point Lap Shear @ 23°C Lap Shear @ 110°C	ASTM D3418 EN 12068 EN 12068	3LPP, FBE 147°C > 600 N/cm <sup>2</sup> > 100 N/cm <sup>2</sup>	Grade <sup>™</sup> coating system.
PP Copolymer Properties Melting point Lap Shear @ 23°C Lap Shear @ 110°C	ASTM D3418 EN 12068 EN 12068	147°C > 600 N/cm² > 100 N/cm²	
Welting point Lap Shear @ 23°C Lap Shear @ 110°C	ASTM D3418 EN 12068 EN 12068	147°C > 600 N/cm <sup>2</sup> > 100 N/cm <sup>2</sup>	ALL PROPERTY OF
Lap Shear @ 23°C Lap Shear @ 110°C	EN 12068 EN 12068	> 600 N/cm <sup>2</sup> > 100 N/cm <sup>2</sup>	
Lap Shear @ 110°C	EN 12068	> 100 N/cm <sup>2</sup>	A CONTRACTOR OF A CONTRACTOR O
PP Top Coat (Backing) Properties			
Tensile Strength	ASTM D638	28 MPa	
Elongation	ASTM D638	> 400%	
Hardness	ASTM D2240	65 Shore D	
Volume Resistivity	ASTM D257	2 x 1017 ohm-cm	
GTS-PP 3LPP Coating System Properties			BAW
Impact Resistance	ISO 21809-1	10 J/mm	Distributors, Inc
ndentation Resistance @ 110°C	DIN 30678	0.4 mm	Authorized Dealer of
Adhesion Strength @ 23°C	ISO 21809-1	> 250 N/cm	Canusa-CPS Products
Adhesion Strength @ 110°C	ISO 21809-1	> 60 N/cm	B&W Distributors, Inc.
Cathodic Disbondment @ 23°C, 28 days	ISO 21809-1	< 3 mm	PO Box 21960
Cathodic Disbondment @ 95°C, 28 days	ISO 21809-1	< 7 mm	Mesa, AZ 852//
Hot Water Immersion @ 95°C, 28 days	ISO 21809-1	Pass, No disbondment	P: 480-924-8883
Total System Thickness	Supplied	Typical Applied	F: 480-924-9100
Standard Product	2.8 mm	> 3.0 mm	info@bwdist.com
Custom project thickness available from 1.5 mm fo	8 mm. Consult with your	r Iocal Canusa Representative.)	Canusa-CPS is registered to ISO 9001:2008

Proven compatibility

and fusion

Canusa warrants that the product conforms to its chemical and physical description and is appropriate for the use stated on the product data sheet when used in compliance with Canusa's written instructions. Since many installation factors are beyond our control, the user shall determine the suitability of the products for the intended use and assume all risks and liabilities in connection therewith. Canusa's liability is stated in the standard terms and conditions of sale. Canusa makes no other warranty either expressed or implied. All information contained in this data sheet is to be used as a guide and is subject to change without notice. This data sheet supersedes all previous data sheets on this product. E&OE

PDS\_GTSPP\_rev037



of configurations to accommodate many specific project applications.

Industry leading

\* Actual temperature rating is dependant on specific project requirements and conditions. Please consult your local Canusa representative.

Since 1967, Canusa-CPS has been a leading developer and manufacturer of specialty pipeline coatings for the sealing and corrosion protection of pipeline joints and other substrates. Canusa-CPS high performance products are manufactured to the highest quality standards and are available in a number

Epoxy usage can be referenced on the Liquid Epoxy, Type P Product Data Sheet.

track record

Exceeds factory-applied

coating standards

