

XCS

Protective Coating for Extreme Conditions, including Cold Weather Applications and Rehabilitation of Pipe Coating

XCS Extreme Condition System utilizes a crosslinked polyolefin backing, coated with a protective heat activated adhesive which effectively bonds to most substrates and common pipeline coatings. XCS is designed to protect live, flowing pipelines where pre-heating of the substrate is not possible. XCS is also designed for cold weather application, as well as custom application and usage. These sleeves are supplied with a black backing that is stabilized against ultra-violet degradation.

Assured Protection

- XCS is made from materials that provide high electrical resistivity, resistance to corrosive environments, low water absorption, low moisture permeability and an effective bond to both the steel surface and to common pipeline coatings.
- When the sleeve is heated, the adhesive is transformed into an amorphous, low viscosity liquid, which has excellent bonding to the substrates.

Flexible & Reliable Installation

- XCS sleeves are available in widths up to 36" (900mm) and can be applied in overlapping sleeve segments along the pipe length, or as a standard field joint coating.
- XCS is available as one-piece wraparound sleeves or as a bulk roll with a separate closure for greater flexibility.

No Pre-Heat

- XCS sleeves can be used to coat live lines operating between 10°C (50°F) and 50°C (122°F).
- No preheat is necessary for ambient temperature installations.



Applications



Repair & Rehab



Mainline Coating



Live Lines



Low Temperature



XCS

Protective Coating for Extreme Conditions, including Cold Weather Applications and Rehabilitation of Pipe Coating

The product information shown here is intended as a guide for standard products.

Consult your Canusa representative for specific projects or unique applications.



Sleeve Operating Characteristics		XCS	
Pipeline Operating Temp.		Up to 50°C (122°F)	
Minimum Installation Temp.		Not Applicable	
Main Line Coating Compatibility		PE, PP, FBE, PU, Coal Tar, Bitumen, Asphalt	
Adhesive Properties	Test Method	Typical Properties	
Softening Point	ASTM E28	110°C	
Lap Shear	DIN 30 672	13 N/cm ²	
Backing Properties			
Tensile Strength	ASTM D638	24 MPa	
Elongation	ASTM D638	700%	
Hardness	ASTM D2240	48 Shore D	
Volume Resistivity	ASTM D257	10 ¹⁷ ohm-cm	
Sleeve Properties			
Adhesion Strength @ 23°C	ASTM D1000	40 N/cm	
Impact Resistance	DIN 30 672	pass	
Indentation Resistance	DIN 30 672	pass	
Cathodic Disbondment @ 23°C, 28 days	ASTM G8	8 mm rad	
Thickness	T	L	S
Backing (nominal thickness as supplied)	0.9 mm (0.035")	0.9 mm (0.035")	1.1 mm (0.045")
Adhesive (nominal thickness as supplied)	0.9 mm (0.035")	1.4 mm (0.055")	1.5 mm (0.060")



**Authorized Dealer of
Canusa-CPS Products**

B&W Distributors, Inc.
PO Box 21960
Mesa, AZ 85277

P: 480-924-8883
F: 480-924-9100

info@bwdist.com
www.bwdist.com

**Canusa-CPS is registered
to ISO 9001:2008**

Canusa warrants that the product conforms to its chemical and physical description and is appropriate for the use stated on the product data sheet when used in compliance with Canusa's written instructions. Since many installation factors are beyond our control, the user shall determine the suitability of the products for the intended use and assume all risks and liabilities in connection therewith. Canusa's liability is stated in the standard terms and conditions of sale. Canusa makes no other warranty either expressed or implied. All information contained in this data sheet is to be used as a guide and is subject to change without notice. This data sheet supersedes all previous data sheets on this product. E&OE

PDS_XCS_rev015

Since 1967, Canusa-CPS has been a leading developer and manufacturer of specialty pipeline coatings for the sealing and corrosion protection of pipeline joints and other substrates. Canusa-CPS high performance products are manufactured to the highest quality standards and are available in a number of configurations to accommodate many specific project applications.