

3M™ Scotchkote™ Liquid Epoxy Coating 323C

Data Sheet and Application Instructions


Product Description

3M™ Scotchkote™ Liquid Epoxy Coating 323C is a two-part system designed as a patch material for 3M™ Scotchkote™ Fusion-Bonded Epoxy Coating 134.

Intended Uses

- As a patch material
- As a girthweld coating
- As an internal lining
- In a wide variety of other field applications where corrosion protection of metal is required

Product Features

- Color match to Scotchkote 134
- No solvents needed
- High build, up to 45 mils/1150 microns in one application
- Applied via cartridge spray and/or 3M™ Scotchkote™ Spray Sytem HSS-450
- Excellent adhesion
- 100% solids
- VOC for Parts A and B as mixed 12 g/L
- Can be applied to a substrate as cold as 41°F/5°C
- Meets the requirements of AWWA C210, 07 clause 5.2.1.1
- Certified to ANSI/NSF Standard 61, Drinking Water System Components 

Chemical Resistance

Scotchkote 323C is resistant to damage by acids and bases in the pH range of 2 to 14. It is also resistant to hydrocarbons such as crude oil, motor oil, gasoline and many solvents. Testing is recommended if the coating is to be used in continual contact with oxidizing agents such as sodium hypochlorite (bleach) and aggressive solvents such as methyl ethyl ketone (MEK).

3M™ Scotchkote™ 323C Coverage per kit size
(Assumes no waste)

Kit	lbs of material		Coverage in square feet @ mils		
	Total	25 mils	28 mils	30 mils	
450 ml	1.34	7.63	6.81	6.36	

General Application Steps

For use as a joint coating, a refurbishing coating or as a pipe coating:

1. Remove oil, grease and loosely adhering deposits.
2. Abrasive blast clean the surface to NACE No. 2/SSPC-SP10, ISO 8501:1, Grade SA 2 1/2 near-white metal.
3. Ensure the abraded surface is cleaned of abrading debris with the use of an air blast or a clean lint free cloth.
4. Within four hours of blasting as per the above cleaning process and with the metal above 41°F/5°C and a minimum of 5°F/3°C above the dew point, apply Scotchkote 323C at a minimum thickness of 635 microns or 25 mils.
5. Allow to cure.
6. Visually or electrically inspect the coating for defects.
7. Repair all defects using Scotchkote 323C as a repair material.

For use as a repair material in the field where scratches or other holidays may have occurred.

1. Remove oil, grease and loosely adhering deposits.
2. Abrade the FBE surface with medium grit sandpaper (approx 80 grit). Powered rotary sanders and sweep blasting are also acceptable means of performing this task as well. Ensure that the surrounding FBE is roughened for 10 mm on all sides of the holiday. An anchor pattern of 40 to 100 microns is preferred on the steel substrate.
3. Ensure the abraded surface is cleaned of abrading debris with the use of an air blast or a clean lint free cloth.



4. With the metal above 41°F/5°C and a minimum of 5°F/3°C above the dew point, apply Scotchkote 323/323i at a minimum thickness of 635 microns or 25 mils.

Properties

Property	Value
Color	Green (color match to Scotchkote 134)
Mix Ratio	2A : 1B by volume 70.8% : 29.2% by weight
Viscosity in cps @	323C
• 72°F/22°C	Part A: 90,000 Part B: 19,000
Shelf Life (unopened container)	24 months
Specific Gravity	1.35 mixed
Coverage	142 ft ² /(lb/mil) (0.74m ² /(kg/mm))
Max Operating Temperature	
• Wet	203°F/95°C
• Dry	250°F/121°C
Minimum Coating Thickness	25 mils/635 microns recommended

Typical Test Properties

Property	Test Description	Typical Value
Shyodu Gel Time (approximate pot life)	200 gm mass	75°F / 24°C 18 Min
		104°F / 40°C 11 min
Dry to Touch Time	ASTM D1640 clause 7.5.2	41°F / 5°C 7 hrs
		75°F / 24°C 1 hr 45 Min
		122°F / 50°C 26 min
Approximate Back Fill Time (For additional information see Shore D Hardness Chart)	ASTM D1640 clause 7.7.1	41°F / 5°C 8 hrs
		75°F / 24°C 2 hr 39 min
		122°F / 50°C 39 min
Cathodic Disbondment (steel grit blasted plates laboratory applied; results may vary depending on blast media)	CSA Z245.20 clause 12.8	149°F / 65°C, 3.5V, 24 hrs 4.9 mmr
		149°F / 65°C, 1.5V, 48 hrs 5.5 mmr
		149°F / 65°C, 1.5V, 28 days 7.5 mmr
		176°F / 80°C, 1.5V, 14 days 6.4 mmr
		176°F / 80°C, 1.5V, 28 days 6.6 mmr
Adhesion of Coating	CSA Z245.20 clause 12.14	203°F / 95°C 24 hrs Rating 1
		167°F / 75°C 48 hrs Rating 1
		167°F / 75°C 28 days Rating 1
Flexibility	CSA Z245.20 clause 12.11	68°F / 20°C 0.7 %PD
		32°F / 0°C 0.7 %PD
Abrasion Resistance	ASTM D4060 CS-17 wheels 1000 g load 5000 cycles wheels resurfaced every 500 cycles	0.325 g loss
Impact Strength	ASTM G14	73.6 inch-lbs (8.3 Joules) at 75°F / 24°C
Impact Resistance	CSA Z245 20 Clause 12.12	See Chart Below

Impact Resistance

Impact value is the last Joule where three impacts have passed

Panel Number	Test Temperature	Joule Value	Holiday detection voltage	Average DFT (mils)
1	-40°F/-40°C	1.5	2500	30.4
3	14°F/-10°C	1.5	2500	27.2
5	68°F/20°C	2.75	2500	26.9
7	149°F/65°C	4.0	2500	27.0

3M™ Scotchkote™ Spray System HSS-450

The application of Scotchkote™ 323C has been simplified using the 3M™ Scotchkote™ Spray System HSS-450. The HSS-450 system utilizes a dual-cartridge setup along with unique application equipment designed specifically to spray apply Scotchkote 323C.



3M™ Scotchkote™ 450 ml Manual gun

An applicator is available to manually dispense Scotchkote™ 323C from the 450 ml cartridge. Static mix nozzles sold separately.



Helpful Cartridge Spray Information

- Preheat cartridge to a temperature in between 120°F – 140°F (49°C - 60°C)

For more information and additional literature on the Scotchkote HSS-450 system, please visit our web site at www.3M.com/corrosion2010 or contact our Customer Service Center at 1-800-722-6721.

Equipment Clean-Up

MEK or toluene may be used to clean spray equipment, rollers and brushes. Utilize proper safety guidelines.



B&W Distributors, Inc. | PO Box 21960 Mesa, AZ 85277 | P: 480-924-8883 | F: 480-924-9100
info@bwdist.com | www.bwdist.com

Handling and Safety Precautions

Read all Health Hazard, Precautionary and First Aid, Material Safety Data Sheet, and/or product label prior to handling or use.

3M and Scotchkote are trademarks of 3M Company.

Important Notice

All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product which are not contained in 3M's current publications, or any contrary statements contained on your purchase order shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.

Warranty; Limited Remedy; Limited Liability.

Because conditions of product use are outside of our control and vary widely, the following is made in lieu of all express or implied warranties: this product will conform to 3M's published product specifications and be free from defects in material and manufacture on the date of your purchase. **3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** If this product is defective upon your receipt, your exclusive remedy shall be, at 3M's option, to replace the 3M product or refund the purchase price of the 3M product. **Except where prohibited by law, 3M will not be liable for any direct, indirect, special, incidental or consequential loss or damage arising from this 3M product, regardless of the legal theory asserted.**



Electrical Markets Division

6801 River Place Blvd.
Austin, TX 78726-9000
www.3M.com/corrosion

Please recycle. Printed in USA.
© 3M 2015. All rights reserved.
80-6111-8518-A