

3M™ Scotchkote™ Purple Patch Compound 323

Data Sheet

Product Description

3M™ Scotchkote™ 323 Purple Patch Compound is an ambient temperature cure, two-part system designed to protect metal, concrete and other surfaces from corrosion and deterioration. Scotchkote 323 Purple Patch Compound is the patch material color matched to 3M Scotchkote 3M™ Scotchkote™ Fusion Bonded Epoxy 426.

Features

- Excellent edge coverage
- No solvents needed
- 100% solids
- Application by cartridge
- Excellent adhesion
- Can be applied to substrate as cold as 41°F / 5°C
- VOC for parts A and B as mixed 12 g/L

General Application Steps

1. Remove oil, grease and loosely adhering deposits.
2. Abrasive blast clean the surface to near-white in accordance with NACE No.2/SSPC-SP 10 near-white metal, ISO 8501-Sa2.5.
3. Ensure the abraded surface is cleaned of debris with the use of an air blaster or a clean lint free cloth.

4. Within 4 hours of blasting as per the above cleaning process and with the metal above 41°F/5°C, apply Scotchkote 323 purple patch compound at the specified thickness.
5. Allow to cure.
6. Visually or electrically inspect the coating for defects.
7. Repair all defects using same material.

*To prevent the formation of rust or oxide, coat as soon as possible after cleaning. For maximum protection, the coating must have direct contact with the metal or parent coating surface.

Repair of Fusion Bonded Epoxy Coating

Scotchkote coating requiring limited repair (scrapes, scars, coating imperfections or other minor defects) should be cleaned to remove dirt, scale and damaged coating by sanding or other suitable means. Feather the adjacent coating and remove all dust by wiping. Next, apply the coating to the clean surface. The freshly coated area should be allowed to properly cure prior to handling and storage. Cure can be accelerated with heat.

Multiple Coats

Scotchkote 323 Purple Patch Compound has been formulated for single coat applications. If additional coats are required, for example edge coverage, apply the additional coats within three hours of the initial coat. This coating may be applied in any thickness consistent with producing an acceptable surface finish.

Typical Properties


Property	Typical Value	
Color	Purple	
Mix Ratio	2 A to 1 B by volume 70.8% : 29.2% by weight	
Shelf Life, unmixed, closed container	24 months	
Viscosity in CPS	Part A: 120,000 Part B: 20,000	
Specific gravity mixed	1.34	
Coverage	50 ml 450 ml	cartridge yields approximately 360 sq. in. @ 8.5 mils cartridge yields approximately 22 sqft @ 8.5 mils



3M™ Scotchkote™ 323 Purple Patch Compound

Property	Test Description	Typical Value			
Shyodu Gel Time (approximate pot life)	200 gm mass	75°F/ 24°C 104°F/ 40°C	17 min 11 min		
Dry to Touch Time	ASTM D1640 clause 7.5.2	41°F/ 5°C 75°F/ 24°C 122°F/ 50°C	7 hrs 1 hrs 45 min 26 min		
Dry to Handle Time	ASTM D1640 clause 7.7.1	41°F/ 5°C 75°F/ 24°C 122°F/ 50°C	8 hrs 2 hrs 39 min 39 min		
Cathodic Disbondment (steel grit blasted plates laboratory applied; results may vary depending on blast media)	CSA Z245.20-98 clause 12.8	149°F/ 65°C 149°F/ 65°C 149°F/ 65°C 176°F/ 80°C 176°F/ 80°C	3.5V 1.5V 1.5V 1.5V 1.5V	24 hrs 48 hrs 28 days 14 days 28 days	4.9 mmr 5.5 mmr 7.5 mmr 6.4 mmr 6.6 mmr
Adhesion	CSA Z245.20-98 clause 12.14	203°F/ 95°C 167°F/ 75°C 167°F/ 75°C	24 hrs 48 hrs 28 days	Rating 1 Rating 1 Rating 1	
Flexibility	CSA Z245.20-98 clause 12.11	68°F/ 20°C 32°F/ 0°C	0.7 0.7	*/PD */PD	
Abrasion Resistance	ASTM D 4060-95 CS-17 wheels 1000 g load 5000 cycles wheels resurfaced every 500 cycles	0.325 g loss			

Scotch 323 Patch Compound Applicator



3M Scotchkote™
AUTHORIZED DISTRIBUTOR

B&W Distributors, Inc.

PO Box 21960
Mesa, AZ 85277

P: 480-924-8883

F: 480-924-9100

info@bwdist.com

www.bwdist.com

Handling and Safety Precautions

Read all Health Hazard, Precautionary, and First Aid statements found in the Material Safety Data Sheet, and/or product label of chemicals prior to handling or use.

3M and Scotchkote are trademarks of 3M Company.

Important Notice

All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product which are not contained in 3M's current publications, or any contrary statements contained on your purchase order shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.

Warranty; Limited Remedy; Limited Liability.

This product will be free from defects in material and manufacture at the time of purchase. **3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. **Except where prohibited by law, 3M will not be liable for any loss or damage arising from this 3M product, whether indirect, special, incidental or consequential regardless of the legal theory asserted.**



Corrosion Protection Products Division

6801 River Place Blvd.
Austin, TX 78726-9000
www.3M.com/corrosion

Please recycle. Printed in USA.
© 3M 2011. All rights reserved.
80-6111-8314-8-B