



PO Box 21960, Mesa Az 85277  
480-924-8883  
info@bwdist.com  
www.bwdist.com

Authorized Distributor of  
CHLOR RID International, Inc.



## **CHLOR\*RID<sup>®</sup>** **LIQUID SOLUBLE SALT REMOVER** ***DIRECTIONS***

---

**DESCRIPTION:** CHLOR\*RID is a unique functional performance product which aids in the removal of chlorides, sulfates, nitrates and other surface reacted soluble salts.

**HIGH PRESSURE WASHING:** CHLOR\*RID is added to the water of the pressure washer, usually in a dilution ratio of 1:100. (See Testing below) Add CHLOR\*RID by means of a metering pump or add to a reservoir water supply. A siphon device may be used, but most such devices lack dilution control and positive input. Use potable water or other approved source. A minimum 3000 p.s.i. pressure washer is recommended. A zero degree rotating nozzle is also recommended. Flush washer and lines prior to application. Can also be applied through UHP waterjetting equipment. Hold pressure nozzle perpendicular to the surface and preferably 4 to 8 inches away to ensure all surfaces are washed with direct high pressure. In areas of deep pitting, slow the wash speed to enable better cleaning. Do not rinse. Typical application rate is 300 to 1000 Sq. Ft. per gallon of CHLOR\*RID.

**HAND WASHING:** Use CHLOR\*RID DTS<sup>™</sup> (Direct To Surface) according to directions. CHLOR\*RID DTS is ready to use direct from the container- no dilution necessary.

**WET ABRASIVE BLASTING:** Add CHLOR\*RID to the system at 1 U.S. gallon per 300-1000 square feet of surface to be blasted using potable water or other approved source. (Dilution ratio of 1:250 typical.) Add CHLOR\*RID to rinse water at 1:250 ratio (or HOLD\*BLAST in a 1:50 dilution ratio to prevent flash rusting). Always use appropriate safety equipment.

**MIST/VAPOR BLASTING:** Add CHLOR\*RID in a 1:100 dilution to the water of the mist blaster. The same water solution may be used for wash down of particulate matter after blasting (or HOLD\*BLAST in a 1:50 dilution ratio to prevent flash rusting).

**TESTING:** After cleaning or blasting a small sample area, test the surface with a CHLOR\*TEST<sup>™</sup> kit to verify cleanliness. Adjust speed of travel, standoff distance, pressure or dilution as necessary and retest to verify desired cleanliness level is attained. Abrasives and water used should be tested with CHLOR\*TEST kits "A" and "W" respectively.

Due to a wide variety of surface conditions, work environments, weather conditions, etc., these directions are general and may require alterations to better suit individual conditions. Call CHLOR RID International Inc. for recommendations for a specific project. CHLOR RID International Inc. assumes no liability for use or misuse of the product inconsistent with its labeling.

**WARRANTY:** CHLOR RID International Inc. warrants this product to be identical in chemical and physical properties from batch to batch within the specification limits of the raw materials used in its manufacture.

**SAFETY PRECAUTIONS:** KEEP OUT OF REACH OF CHILDREN. Do not mix with other chemicals. See M.S.D.S. for full precautions before use. This product is intended for professional use only.